## PATENT ABSTRACTS OF JAPAN

(11)Publication number:

11-312418

(43) Date of publication of application: 09.11.1999

(51)Int.CI.

H01B 3/44

CO8L 23/00

CO8L 53/02

H01B 7/34

(21)Application number: 10-117478

(71)Applicant: FURUKAWA ELECTRIC CO LTD:THE

(22)Date of filing:

27.04.1998

(72)Inventor: HASHIMOTO MASARU

**NISHIGUCHI MASAMI** 

YAMADA HITOSHI TASAKA MICHIHISA

KAJIYAMA SATOYUKI


SAITO SHINZO

## (54) INSULATED ELECTRIC WIRE

## (57)Abstract:

PROBLEM TO BE SOLVED: To provide an insulated electric wire, having high flame retardancy, having excellent mechanical characteristics and heat resistance, capable of being colored arbitrarily, not whitened if folded or wound, and causing neither elution of heavy-metal compounds nor generation of large amounts of smoke and corrosive gases when disposed such as by land filling or incineration.

SOLUTION: This insulated electric wire has a primary coating layer 2 made of a flame retardant resin composition provided around a conductor 1 and a secondary coating layer 3 made of a flame retardant resin composition provided around the primary coating layer 2. The primary coating layer 2 is formed from a resin composition made by blending a metal hydrate of 80 to 140 pts.wt. and red phosphorus of 2.5 to 14.5 pts.wt. with a polyolefine resin of 100 pts.wt., and the secondary coating layer 3 is formed from a flame retardant resin composition made by blending an ammonium polyphosphate flame retarder of 20 to 80 pts.wt. with a specific vinyl aromatic thermoplastic elastomer resin composition of 100 pts.wt.



## **LEGAL STATUS**

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

{Date of requesting appeal against examiner's

decision of rejection]

{Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office